

EPDM BONDING ADHESIVE LVOC

Item Description

5 Gallon (18.9 Liter)

Item Number

W590010174

Product Information

Description

GenFlex EPDM Bonding Adhesive LVOC is a contact adhesive designed specifically for bonding GenFlex EPDM membranes and flashings to GenFlex insulations, wood, metal, masonry and other acceptable substrates.

Method of Application

1. Surfaces to receive GenFlex EPDM Bonding Adhesive LVOC shall be clean, smooth, dry, free of sharp edges, loose and foreign materials, oil, grease, and other contaminants. Sweep the mating surface of the membrane with a stiff broom to remove excess dusting agent, if present, or other contaminants from the mating surface.
2. Stir the adhesive thoroughly before and during use, achieving a uniform mix with no sediment on the bottom and no marbling evident.
3. Apply adhesive at about the same time to both the exposed underside of the sheet and the substrate to allow approximately the same flash-off time.
4. Apply by rolling the adhesive on both mating surfaces. GenFlex EPDM Bonding Adhesive LVOC should be applied evenly so as to avoid globs or puddles.
5. As an option, spray GenFlex EPDM Bonding Adhesive LVOC and back-roll the adhesive uniformly and evenly with a solvent-resistant paint roller. **Care must be taken not to apply adhesive over any area that will later be cleaned and spliced to another sheet or flashing.**
6. Allow GenFlex EPDM Bonding Adhesive LVOC to flash off until tacky. Touch the adhesive surface with a clean, dry finger to be certain that the adhesive is dry and does not stick or string. While pushing straight down to check for stringing, also push forward on the adhesive at an angle to ensure that the adhesive is ready (flushed off) throughout its thickness. If either motion exposes wet or stringy adhesive when the finger is lifted, then it is not ready for mating. Flash-off time will vary depending on ambient air conditions.
7. Starting at the fold, roll the previously coated portion of the sheet into the coated substrate slowly and evenly so as to maintain position and minimize wrinkles. To ensure proper contact, compress the bonded half of the sheet to the substrate with a stiff push broom using heavy pressure immediately after mating membrane to substrate.

Storage

- Store in original unopened containers at temperatures between 60 °F (16 °C) and 80 °F (27 °C) until ready for use. In colder weather, product must be used within four hours of transport to the roof. Return unused material to warm storage for a minimum of 24 hours.
- For optimum results, rotate stock to ensure stored material has not exceeded the shelf life of one year.
- Shelf life of one year can be expected if stored in original sealed container at temperatures between 60 °F (16 °C) and 80 °F (27 °C). If exposed to lower temperatures, restore to room temperature prior to use.
- Shelf life will be shortened if exposed to elevated temperatures.

Precautions

- Flammable. Keep away from fire and open flame and other possible ignition sources during storage and use. Do not smoke when using.
- Harmful or fatal if swallowed.
- Avoid prolonged inhalation.
- Avoid prolonged contact with skin. Gloves should be worn (OSHA approved).
- Avoid eye contact by wearing safety glasses with side shields or safety goggles.
- For professional use only.
- Keep out of reach of children.
- Thinning is not allowed.
- Do not use for splicing.
- Do not use with fleece backed membranes.
- Use only in well ventilated areas.
- Cover tightly when not in use.
- Review Safety Data Sheet (SDS) prior to use.
- Recommended cleaner is Toluene (while fluid).

LEED® Information

Recycled Content:
 Post-Consumer 0%
 Post Industrial 0%
 Manufacturing Location: South Bend, IN
 *NOTE: LEED® is a registered trademark of the U.S. Green Building Council



Typical Properties	
Property	Typical Performance
Base	Polychloroprene Rubber
Color	Yellow
Solvents	Tert-butyl Acetate; Ethyl Acetate
Solids by Volume	22%
Viscosity	2,500-3,500 cP, R.V.F. Brookfield, #3 Spindle @ 10 RPM
Weight	7.8 ± 0.20 lb/gal
Specific Gravity	0.93 ± 0.20
V.O.C. Content	Actual VOC content, less water and exempt solvents (including Tert-Butyl Acetate) is less than 250 grams/liter as supplied, and is considered VOC exempt in jurisdictions recognizing such exempt solvents.

Packaging Data	
Pail	5 gal (18.9 L)
Weight	41 lb (18.6 kg)
Coverage	A coverage rate of 45 - 60 ft ² /gal (1.10 – 1.47 m ² /L) may be obtained depending on the substrate. Some insulation surfaces are more uneven and porous and will result in a lower coverage rate while smooth non-porous substrates will result in higher coverage rates. Rates are based on roller application to both mating surfaces. Very porous substrates (rough wood, concrete block) may require <u>two</u> coats of EPDM Bonding Adhesive LVOC to ensure proper adhesion. This can be determined by adhering a small piece of membrane to the porous substrate to verify the bonding strength.
Units per Pallet	45 – 5 gal pails

Approved Power Application Equipment:

Graco Spray Equipment:

287975 30:1 Xtreme® pneumatic pump with Air Assisted Airless package, (1000 psi operating pressure)
Hopper and pump mounted to Heavy Duty Cart, 287884, 288347 Hopper Kit, 222695 Agitator to be mounted by customer,
249133, 249256, 249180 Air Cap for G40 Applicator (800 psi min. fluid atomization; air pressure 80 psi)
GG4321, GG4421 tips

Garlock 2120 Commander Sprayer

18 hp Kohler Engine, 4500 psi Rating, Pump Displacement 45:1, GPM Rating: up to 5 gpm, ½" x 100' hose, 2" Intake pipe with screen 5 or 55 gal drum containers, Graco Spray Tips: .019 to .025 diameter hose (26000 psi operating pressure)

Garlock Twin Gun Airless Sprayer

6.5 hp Honda Engine, 3000 psi Rating, Pump Displacement 30:1, GPM Rating: up to 1 ½ gpm, Up to 400' of single ½" diameter hose, Up to 200' of dual ½" diameter hose, ½" Intake pipe with screen, 5 or 55 gal drum containers, Bulk tank containers, Graco Spray Tips: .019 to .025 diameter hose (1850 psi operating pressure)

Please contact Quality Building Services Technical Department at 1-800-443-4272 option 1, for further information.

This sheet is meant to highlight GenFlex products and specifications and is subject to change without notice. GenFlex takes responsibility for furnishing quality materials which meet published GenFlex product specifications. Neither GenFlex nor its representatives practice architecture. GenFlex offers no opinion on and expressly disclaims any responsibility for the soundness of any structure. GenFlex accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No GenFlex representative is authorized to vary this disclaimer.