

**GenFlex FlexWhite™
Peel & Stick™ Flashing**

DESCRIPTION

GenFlex FlexWhite™ Peel & Stick™ Flashing consists of semi-cured flashing that is factory laminated to cured seam tape. It is designed to flash inside and outside corners, pipes, penetration pockets and other applications as required by GenFlex specifications.

It is available in 12" (304 mm) wide by 25' (7.6 M) long rolls.

PHYSICAL PROPERTIES

SEAM TAPE PROPERTY	MINIMUM SPECIFICATIONS
Base	Rubber Polymer
Color	White
Solvents	None
Percent Solids	100%
Cure State	Cured
Thickness	.025" (.635 mm) ± .007" (± .18 mm)
Width	12 ¼" (311 +0 / -1/18" (-1.6 mm)
Length	25' (7.6 m)

FLASHING PROPERTY	MINIMUM SPECIFICATIONS
Base	EPDM
Color	White
Solvents	None
Percent Solids	100%
Cure State	Uncured
Thickness	.060" (1.6mm) ± .005" (± .13 mm)
Width	12" (304.8 mm) +0 / -1/18" (-1.6 mm)
Length	25' (7.6 m)

INSTALLATION

1. Thoroughly mix GenFlex Clear Primer (DO NOT THIN) a minimum of 2 minutes of vigorous hand mixing with a wooden paint stirrer or its equivalent is required. All sources of ignition should be eliminated and adequate ventilation should exist.
2. Clean all surfaces with a clean cotton rag and Cleaner to remove excessive dirt or contamination prior to application of the primer.
3. With a scrub pad and handle, apply GenFlex Clear Primer using long and continuous back and forth strokes with heavy to moderate pressure along the bonding area until no streaks or puddling occurs.
4. Allow GenFlex Primer to dry until slightly tacky to a dry finger touch.
5. Cut the Peel & Stick Flashing to the desired size to fit the specific detail.
6. Remove release paper from the flashing and apply it to the primed area using care not to over stretch or thin out the flashing material.

7. Using Teflon coated or hard rubber roller, hand-roll the flashing firmly to ensure uniform contact. Pay special attention to any over lap areas or step downs and field seam intersections.
8. Apply a continuous "high profile" bead of Edge Caulk at all overlaps and field seam intersections. All details will be completed per current GenFlex Specifications.

INSTALLATION - PRECAUTIONS

1. When cloudy conditions below 60°F (15.6°C) occur, use heat guns (without ignition sources) to heat FlexWhite Peel & Stick Flashing. This will ensure good formability of the flashing to the primed substrate.
2. On sunny days less than 70°F (21.1°C), place FlexWhite Peel & Stick Flashing on roof (prior to application) with flashing side up to allow it to warm up ensuring good formability.
3. On sunny days greater than 70°F (21.1°C), place FlexWhite Peel & Stick Flashing on roof (prior to application) with release paper side up to prevent it from gaining too much heat and to ensure goof formability.

PRODUCT DATA

SIZE	QUANTITY	PRODUCT #
12" x 25' (304.8 mm x 7.6 m)	1 Roll	W590030091

Each package contains GenFlex Scrub Pads and Handles.

LEED INFORMATION

Post Consumer Recycled Content	0%
Post Industrial Recycled Content	0%

STORAGE

Store in original unopened container indoors at temperatures between 60°F (16°C) and 80°F (27°C). Do not store on roof in direct sunlight or at temperatures above 100°F (38°C). When exposed to lower temperatures, restore to room temperature prior to use.

Do not store in direct sunlight or at temperatures above 80°F (27°C).

When exposed to lower temperatures, restore to room temperature prior to use.

Keep dry prior to use.

SHELF LIFE

Shelf Life of one year can be expected when stored at 60° F (15.6° C) and 80° F (26.7° C) in original unopened containers indoors. Shelf life will be shortened if exposed to elevated temperatures.

PRECAUTIONARY DATA



250 West 96th Street, Suite 150 Indianapolis, IN 46260
800-443-4272 • www.genflex.com

PRODUCT DATA SHEET

GenFlex FlexWhite™ Peel & Stick™ Flashing

Take care when moving, transporting, and handling, etc. to avoid sources of punctures and physical damage.

Contact GenFlex Roofing Systems Technical Department for specific recommendations.

Refer to Material Safety Data Sheet for additional information.