

TPO REINFORCED OUTSIDE CORNER

Item Description

12" x 12" (304.8 mm x 304.8 mm)
 Thickness .045" (1.1 mm) ± 10%
 White
 Grey
 Tan

Item Number

W590030270
 W590030271
 W590030272



Product Information

Description

GenFlex TPO Reinforced Outside Corners are factory fabricated corners made from high performance TPO roofing membrane. The large 12" x 12" (304.8 mm x 304.8 mm) design allows the flashing to conform to irregular corners or conditions found at the jobsite. Factory welds decrease installation time and improve long-term watertight performance.

Typical Properties		
Property	Test Method	Typical Values
Color	---	White, Grey, Tan
Nominal Thickness	ASTM D 638	.045"(1.1 mm)
Tensile at Break	ASTM D 751	1500 psi (10 MPa)
Tear Resistance	ASTM D 751	350 lb/in (15 kN)
Dimensional Stability	ASTM D 1204	± 0.3%

Installation

Refer to current GenFlex Technical Specifications for additional instructions.

IMPORTANT: Ensure the receiving surfaces are free of debris and no moisture is present.

1. Application of GenFlex TPO Reinforced Corners must be conducted in accordance with current heat welding instructions per GenFlex TPO Technical Specifications.
2. Heat weld TPO Reinforced Corners over angle changes or intersection areas between field membrane and appropriate vertical flashings. Corners should be centered on outside corner areas and welded using approved cleaning and heat welding techniques and equipment.
3. Aged or weathered TPO membranes will require additional cleaning with GenFlex Cleaner in order to remove dirt or debris from the welding area.
4. Refer to the Product Data Sheet for GenFlex Cleaner for additional information on the proper use and application of the cleaner.
5. When exposed to lower temperatures, restore to room temperature prior to use.

*LEED® Information

Recycled Content

Post Consumer 0%

Post Industrial 1.3%

*NOTE: LEED® is a registered trademark of the U.S. Green Building Council.

Storage

- Store in original unopened container indoors at temperatures between 60 °F (16 °C) and 80 °F (27 °C). Do not store on roof in direct sunlight or at temperatures above 100 °F (38 °C). When exposed to lower temperatures, restore to room temperature prior to use.
- Do not store in direct sunlight or at temperatures above 80 °F (27 °C).

Precautionary Data

- Take care when moving, transporting, and handling, etc., to avoid sources of punctures and physical damage.
- Contact GenFlex Systems Technical Department for specific recommendations.
- Refer to Safety Data Sheet for additional information.

Please contact GenFlex Technical Services at 1-800-443-4272 option 1, for further information.

This sheet is meant to highlight GenFlex products and specifications and is subject to change without notice. GenFlex takes responsibility for furnishing quality materials which meet published GenFlex product specifications. Neither GenFlex nor its representatives practice architecture. GenFlex offers no opinion on and expressly disclaims any responsibility for the soundness of any structure. GenFlex accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No GenFlex representative is authorized to vary this disclaimer.