

GenFlex FlexWhite Peel and Stick EPDM Flashing

Item Description

12" x 25' (304.8 mm x 7.6 m)

Item Number

W590030091



Product Information

Description

GenFlex FlexWhite™ Peel & Stick™ EPDM Flashing is a semi-cured white EPDM flashing laminated to a cured tape. FlexWhite Peel & stick EPDM flashing is specifically designed to be used in FlexWhite EPDM and TPO roofing applications for flashing pipes and other field fabricated flashing details.

Typical Properties - EPDM

Property	Typical Values
Color	White
Base	EPDM
Solids	100%
Cure State	Semi-cured
Thickness	0.06" (1.5 mm) ± 10%

Typical Properties - Tape

Property	Typical Values
Color	White
Base	Rubber Polymer
Solids	100%
Cure State	Cured
Thickness	0.025" ± 0.007" (0.635 mm ± 0.18 mm)

Installation

Refer to current GenFlex Technical Specifications for additional application instructions.

IMPORTANT: Ensure both mating surfaces are free of debris and no moisture is present on the splicing surfaces.

1. Thoroughly mix GenFlex FlexWhite Clear Primer. **DO NOT THIN!** A minimum of 2 minutes of vigorous hand mixing with a wooden paint stirrer or its equivalent is required. All sources of ignition should be eliminated; adequate ventilation should exist.

2. Clean all surfaces with a clean cotton rag removing excess dirt or contamination prior to application of the primer.
3. With a GenFlex scrub pad and handle, apply GenFlex FlexWhite Clear Primer using long and continuous back and forth strokes with heavy to moderate pressure along the bonding area until no streaks or puddling occurs.
4. Allow GenFlex FlexWhite Clear Primer to dry until slightly tacky to a dry finger touch.
5. Cut the FlexWhite Peel & Stick Flashing to the desired size to fit the specific detail.
6. Peel off the release paper from the flashing and apply it to the primed area. Use care not to over stretch or thin out the flashing material.
7. Using Teflon coated or hard rubber roller, hand-roll the flashing firmly to ensure uniform contact. Pay special attention to any factory seam step downs and field seam intersections.
8. Apply a continuous "high profile" bead of FlexWhite Edge Caulk to the entire edge of the FlexWhite Flashing per current GenFlex Technical specifications.

Product Data

Size	Contents	Product #
12" x 25' (304.8 mm x 7.6 m)	1 Roll per Carton	W590030091
NOTE: Each package contains GenFlex Scrub Pads and Handles		

*LEED® Information

Recycled Content

Post Consumer	0%
Post Industrial	0%

*NOTE: LEED® is a registered trademark of the U.S. Green Building Council.

Storage

Store indoors in original unopened containers at a temperature between 60 °F and 80 °F (16 °C and 27 °C) for maximum shelf life. Do not store products on the roof in direct sunlight or at temperatures above 100 °F (38 °C). When exposed to lower temperatures, restore to room temperature prior to use.

Shelf Life

6 months; shelf life will be shortened if exposed to elevated temperatures.

Precautionary Data

- To avoid sources of punctures and physical damage, take care when moving, transporting, or handling, etc. to avoid sources of punctures and physical damage.
- Contact GenFlex Roofing Systems Technical Department for specific recommendations.
- Refer to Material Safety Data Sheet for additional information.
- FlexWhite Peel & Stick EPDM Flashing is semi-cured. Do not stretch.

Please contact GenFlex Technical Services at 1-800-443-4272, option 1, for further information.

This sheet is meant to highlight GenFlex products and specifications and is subject to change without notice. GenFlex takes responsibility for furnishing quality materials which meet published GenFlex product specifications. Neither GenFlex nor its representatives practice architecture. GenFlex offers no opinion on and expressly disclaims any responsibility for the soundness of any structure. GenFlex accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No GenFlex representative is authorized to vary this disclaimer.