

## GENFLEX Quick Jet Adhesive

### Item Description

Quick Jet Adhesive Canister

### Item Number

W59RACSADC

#### **Application Accessories** (sold separately)

LVOC Canister Flush Solution (refer to PDS #839)

W59RAC1696

Spray Gun (for vertical application)

W56RACINTH

Spray Gun with Extension (for horizontal application)

W56RACINTI

60° Spray Tip - 5 pack

W56RACINTJ

Canister Hose - 6' (1.83 m)

W56RACIAPRL

Canister Hose - 12' (3.66 m)

W56RACIAPRM

Canister Hose - 18' (5.49 m)

W56RACIAPRN

## Product Information

### Description

Quick Jet Adhesive is an LVOC bonding adhesive packaged in portable, pressurized canisters and formulated for two-sided spray application directly from the canister. Quick Jet provides excellent adhesion of GenFlex EPDM, FlexWhite™ EPDM, EZ TPO and EZ Fleece Backed TPO roofing membranes and flashings to approved substrates in both horizontal and vertical applications.

### General Application Information:

1. Dispense Quick Jet Adhesive in a well-ventilated area using appropriate personal protective equipment (PPE). The use of 3rd party dispensing systems is not approved.
2. Surfaces to receive Quick Jet Adhesive must be clean, smooth, dry, free of sharp edges, loose and foreign materials, oil, grease, and other contaminants. Avoid contact with asphalt surfaces.
3. The Quick Jet canister must be at least 70 °F (21 °C) at the time of application. Adhesive may be applied at ambient temperatures as low as 25 °F (-4 °C) and rising, but canister temperature must be a minimum of 70 °F (21 °C).
4. Do not apply Quick Jet in windy conditions exceeding 15 MPH (or when flag is standing straight out.). A wind break may be necessary to maintain fan spray pattern in winds less than 15 MPH.
5. Apply adhesive at about the same time to both the membrane and the substrate to allow approximately the same flash-off time.
6. Make sure the trigger lock on adhesive spray gun (if equipped) is engaged when not in use to prevent accidental discharge.
7. Refer to the Quick Jet Application Guide for specific application instructions.

### Quick Jet Spray Applicator Assembly:

1. Connect the hose to the gun and tighten fitting securely with wrench. Connect the other end of the hose to the Quick Jet Adhesive cylinder outlet and tighten fitting securely with wrench. Use caution not to cross-thread the connections.
2. Open the cylinder valve fully, checking all connections for leaks. Tighten if necessary.
3. Once the valve has been opened, do not close the valve until the cylinder is completely empty or hose and spray gun are to be removed and proper cleaning is performed. Refer to the Quick Jet Application Guide for additional information.
4. The spray tip may require periodic cleaning.
5. Agitate Quick Jet canister for 30 seconds prior to use. Periodically shake the canister during application to maintain canister pressure and produce optimal fan spray pattern.

### Shelf Life

Shelf life of one (1) year can be expected when stored in original container at temperatures between 60 °F (16 °C) and 80 °F (27 °C).

**Storage**

- Store canister tightly closed, without gun/hose assembly attached, in a cool, dry, well-ventilated area, between 60 °F and 80 °F (16 °C – 47 °C).
- Bring canister to 70 °F (21 °C) before application. Do not allow canister temperature to exceed 110 °F (43 °C).
- For best results, use partially dispensed adhesive canisters within 60 days.

**Coverage Rate:**

- Approximately 1000 ft<sup>2</sup>/canister (92.9 m<sup>2</sup>/canister) for smooth-backed membranes
- Approximately 750 ft<sup>2</sup>/canister (69.7 m<sup>2</sup>/canister) for EZ Fleece Backed TPO membrane

**Packaging Data**

<b>Quick Jet Canister</b>	Packaged Weight: 45 - 48 lb (20.4 - 21.7 kg) per canister. <b>NOTE:</b> Application accessories (cleaning solution, spray guns, hoses, tips) sold separately
---------------------------	---

**Precautions**

- Review applicable Safety Data Sheets (SDS) prior to use.
- Avoid contact with eyes. Wear safety glasses with side shields.
- Avoid breathing vapors. Spray in well ventilated areas.
- Avoid contact with skin. Wear gloves when dispensing. Wash hands thoroughly after handling.
- Close canister valves when not in use.
- Do not sit or stand on cartons or canisters.
- Do not expose product to open flame or temperatures above 110 °F (43 °C).
- Canisters and contents must be brought to temperature between 70 °F – 90 °F (21 – 32 °C) for use.
- Keep canisters in upright position while dispensing adhesive.
- Do not dispense adhesive in areas of spark, open flame or other ignition sources. Do not smoke in areas where Quick Jet Adhesive is being applied.

**LEED® Information**

Post-Consumer Recycled Content: 0%

Post Industrial Recycled Content: 0%

Manufacturing Locations: South Bend, IN - Houston, TX

\*NOTE: LEED® is a registered trademark of the U.S. Green Building Council.

Typical Properties		
Property	Test Method	Typical Values
Base	----	Synthetic Polymers
Color	----	Clear to hazy amber yellow
Viscosity	ASTM D2196	50-200 cPs @ 68 °F (20 °C)
Density	ASTM D1875	7.05-7.22 lb/gal (0.845-0.865 kg/l)
V.O.C. Content	----	<250 grams/liter

Please contact Technical Services at 1-800-443-4272 option 1, for further information.

*This sheet is meant to highlight GenFlex products and specifications and is subject to change without notice. GenFlex takes responsibility for furnishing quality materials which meet published GenFlex product specifications. Neither GenFlex nor its representatives practice architecture. GenFlex offers no opinion on and expressly disclaims any responsibility for the soundness of any structure. GenFlex accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No GenFlex representative is authorized to vary this disclaimer.*