

## GenFlex EX TPO Clear Cut Edge Sealant

### Item Description

16 oz (473 cm<sup>3</sup>) squeeze bottle with reusable conical tips

### Item Number

W59TPOC002



## Product Information

### Description

GenFlex EZ TPO Clear Cut Edge Sealant is a polymer-based sealant that is used as a sealing agent on cut edges of the TPO membrane after they are heat welded. It offers good adhesion to TPO membrane and other surfaces.

Typical Properties	
Property	Typical Values
Color	Clear
Solid Contents	28 – 32%
Cure Time	24 Hours
Tack Free Time	4 Hours
Weight	7.35 – 7.45 lb
VOC Content	611 g/L
Base	Synthetic Rubber
Viscosity	3,000 – 4,000 cps

### Installation

Please consult current GenFlex TPO specifications and details for specific applications.

1. Surfaces to be sealed must be dry and free from dust, oil, water and other contaminants.
2. If seam area is contaminated, use a clean rag saturated with GenFlex Cleaner, thoroughly clean an area on both sheets at least 2" (51 mm) each way from the edge of the seam.
3. Shake bottle well before using. Cut approximately ¼" (6.4 mm) of the tip of the plastic squeeze bottle. Apply ⅛" (3.175 mm) bead of TPO Sealant to the cut edge of the TPO membrane. Ensure bead covers entire edge. The GenFlex EZ TPO Clear Cut Edge Sealant can be used at 20 °F (-6.67 °C) and rising if blushing is not present.

**Note:** Allow sealant to dry to tack-free state prior to inclement weather. All splices shall be caulked before day's end. Caulk is required for exposed cut edges of the TPO membrane.

## Product Data

Typical Properties	
Quantity	12 – 16 oz (473 cm <sup>3</sup> ) squeeze bottles per carton with reusable conical tips, 60 cartons per pallet
Bottle	1 pint (0.47 L)
Carton Weight	13 lbs (5.9 kg)
Coverage Rate	$\frac{1}{8}$ " (3.175 mm) diameter bead: 188 lf/pt (57 m/0.47L) $\frac{1}{4}$ " (6.35 mm) diameter bead: 50 lf/pt (15.2 m/0.47L)

### \*LEED® Information

#### Recycled Content

Post-Consumer: 0%

Post Industrial: 0%

Manufacturing Location: Akron, OH

\*NOTE: LEED® is a registered trademark of the U.S. Green Building Council.

### Storage

Store indoors in original unopened containers at a temperature between 60 °F and 80 °F (16 °C and 27 °C) for maximum shelf life. Do not store on roof in direct sunlight. When exposed to lower temperatures, restore to room temperature prior to use.

### Shelf Life

- Shelf life of one (1) year can be expected when stored in original, sealed container and at temperatures between 60 °F and 80 °F (15.6 °C and 26.7 °C).
- Shelf life will be shortened if exposed to elevated temperatures for a prolonged period of time.

### Precautionary Data

- Review Safety Data Sheets (SDS) prior to use.
- Flammable. Keep away from open flames during storage and use. Do not smoke when using.
- Use only in well ventilated areas.
- Cover tightly when not in use.
- Do not contaminate with foreign materials.
- Do not thin.
- GenFlex EZ TPO Clear Cut Edge Sealant is **not** to be used for splicing or as a general-purpose caulking.

Please contact GenFlex Technical Services at 1-800-443-4272 option 1, for further information.

*This sheet is meant to highlight GenFlex products and specifications and is subject to change without notice. GenFlex takes responsibility for furnishing quality materials which meet published GenFlex product specifications. Neither GenFlex nor its representatives practice architecture. GenFlex offers no opinion on and expressly disclaims any responsibility for the soundness of any structure. GenFlex accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No GenFlex representative is authorized to vary this disclaimer.*