


SBS FR Torch

Item Description

1 Roll - White (1 square)

Item Number

W81PWP16FT2N



Product Information

Description

GenFlex SBS FR Torch is a modified bitumen membrane featuring a blend of SBS (Styrene-Butadiene-Styrene) rubber polymer and high-quality asphalt reinforced with a 190 g/m² (3.89 lb/100 ft²) strong non-woven polyester mat enhanced with continuous fiberglass yarns. The addition of SBS rubber polymer and fire-retardant materials optimizes the asphalt blend to increase its natural waterproofing properties, adding elongation, elasticity, flexibility and resistance to fire. The fiberglass-reinforced polyester mat provides strength and stability to the product, yielding a membrane that resists natural forces and other factors on the rooftop. SBS FR Torch is designed specifically as the top layer for use with GenFlex SBS Modified Bitumen Systems and has the bottom surface covered with a poly burn-off film to aid in heat welding applications. GenFlex SBS Systems are ideal for use on both new construction and re-roofing projects.

NOTE: Meets or exceeds performance requirements of ASTM D 6164, Type I, Grade G.

Product Packaging	
Property	Value
Roll Width	3 ft 3 in (1 m)
Roll Length	32 ft 10 in (10 m)
Net Coverage	98 ft ² (9.1 m ²)
Pallet Size	48 x 39 in (1.2 x 1 m)
Rolls Per Pallet	20
Roll Weight	116.5 lb (52.84 kg)
Weight per Pallet	2,330 lb (1,056.87 kg)

Installation

Refer to current GenFlex Technical Specifications for additional instructions.

IMPORTANT: Ensure the receiving surfaces are free of debris and no moisture is present.

1. SBS FR Torch shall be installed by fully heat welding the membrane to an appropriate substrate.
2. Please reference the Asphalt Roofing Systems Guide for Applicators and Designers available on our website for detailed information regarding the application of SBS FR Torch.

Acceptable Immediate Substrates for Heat-Welded Application

- Structural Concrete (must be clean, dry, properly cured, and primed with ASTM D-41 primer).
- Approved GenFlex base sheet.
- Existing Smooth Surface BUR or SBS Modified Bitumen (must be clean, smooth and primed with ASTM D-41 primer)
- DensDeck® Prime, SECUROCK Gypsum Fiber.

NOTE: Please reference the Asphalt Roofing Systems Guide for Applicators and Designers available on our website for detailed information regarding the type of deck and insulation in use.

Storage

- All material should be stored out of the weather in a clean, dry area in its original unopened packaging at a minimum of 50 °F (10 °C) and a maximum of 100 °F (38 °C) so that it will be 50 °F (10 °C) or above at the time of application.
- Do not stack SBS FR Torch more than two (2) pallets high.
- If the material must be stored temporarily on the roof before application, it must be elevated from the roof surface on a pallet, stored on end, and covered from the weather with a light-colored opaque tarp in a neat, safe manner that does not exceed the allowable load limit of the storage area.

Precautions

- Take care when transporting and handling Modified Bitumen rolls to avoid punctures and other types of physical damage.
- Isolate waste products, petroleum products, grease, oil (mineral and vegetable) and animal fats from all Modified Bitumen membranes.
- Refer to Safety Data Sheets (SDS) for additional safety information.

*LEED® Information

Recycled Content

Post-Consumer

3%

Post Industrial

0%

Manufacturing Location

Beech Grove, IN



*NOTE: LEED® is a registered trademark of the U.S. Green Building Council.

Typical Properties

Property	Test Method	ASTM Standard Required Value	Typical Performance
Product Thickness	D 5147	130 mil (3.3 mm)	160 mil (4.1 mm)
Net Mass	D 146	75 lb/100 ft ² (3,661 g/m ²)	90 lb/100 ft ² (4,394 g/m ²)
Bottom Side Coating	D 5147	40 mil (1.02 mm)	43 mil (1.1 mm)
Peak Load at 0 °F (-18 °C)	D 5147	70 lbf/in, MD (12.3 kN/m) 70 lbf/in, XMD (12.3 kN/m)	80 lbf/in, MD (14 kN/m, MD) 80 lbf/in, XMD (14 kN/m, MD)
Elongation at Peak Load at 0 °F (-18 °C)	D 5147	20%, MD 20%, XMD	50%, MD 50%, XMD
Peak Load at 73 °F (23 °C)	D 5147	50 lbf/in, MD (8.8 kN/m) 50 lbf/in, XMD (8.8 kN/m)	55 lbf/in, MD (9.6 kN/m) 55 lbf/in, XMD (9.6 kN/m)
Elongation at Peak Load at 73 °F (23 °C)	D 5147	35%, MD 35%, XMD	50%, MD 50%, XMD
Ultimate Elongation at 5% of Peak Load 73 °F (23 °C)	D 5147	38%, MD 38%, SMD	60%, MD 60%, XMD
Tear Strength at 73 °F (23 °C)	D 5147, D 4073	55 lbf, MD (246 N) 55 lbf, XMD (246 N)	60 lbf, MD (267 N, MD) 60 lbf, XMD (267 N, MD)
Low Temperature Flexibility	D 5147	0 °F (-18 °C)	-15 °F (-26 °C)
Dimensional Stability	D 5147, D 1204	1% Change, MD 1% Change, XMD	0.2% Change, MD 0.2% Change, XMD
Compound Stability	D 5147	215 °F (102 °C)	250 °F (121 °C)
Granule Loss	D 4977	2 g	0.5 g

NOTE: The initial SRI for standard white membrane is 33.

Please contact GenFlex Technical Services at 1-800-443-4272 option 1, for further information.

This sheet is meant to highlight GenFlex products and specifications and is subject to change without notice. GenFlex takes responsibility for furnishing quality materials which meet published GenFlex product specifications. Neither GenFlex nor its representatives practice architecture. GenFlex offers no opinion on and expressly disclaims any responsibility for the soundness of any structure. GenFlex accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No GenFlex representative is authorized to vary this disclaimer.