

GENFLEX ISO INSULATION

THICKNESS [INCHES]	LTTR	SHEETS PER BUNDLE*
0.50	2.9	96
1.00	5.7	48
1.10	6.3	43
1.20	6.8	40
1.25	7.1	38
1.30	7.4	36
1.40	8.0	34
1.50	8.6	32
1.60	9.1	30
1.70	9.7	28
1.75	10.0	27
1.80	10.3	26
1.90	10.8	25
2.00	11.4	24
2.10	12.0	22
2.20	12.6	21
2.25	12.9	21
2.30	13.2	20
2.40	13.8	20
2.50	14.4	19
2.60	15.0	18
2.70	15.6	17
2.75	15.9	17
2.80	16.2	17
2.90	16.8	16
3.00	17.4	16
3.10	18.0	15
3.20	18.6	15
3.25	18.9	14
3.30	19.2	14
3.40	19.9	14
3.50	20.5	13
3.60	21.1	13
3.70	21.7	12
3.75	22.0	12
3.80	22.3	12
3.90	23.0	12
4.00	23.6	12
4.10	24.2	11
4.20	24.9	11
4.25	25.2	11
4.30	25.5	11
4.40	26.1	10
4.50	26.8	10

* May vary based on facer type used



LEARN MORE

LTTR REFERENCE CARD



GENFLEX HD ISO

GRADE	LTTR	SHEETS PER BUNDLE
Grade 1 (109 PSI MAX)	2.5	46
Grade 2 (139 PSI MAX)	2.5	46

GENFLEX HD COMPOSITE ISO

THICKNESS [INCHES]	LTTR	SHEETS PER BUNDLE
1.50	8.2	32
1.75	9.6	27
2.00	11.1	24
2.20	12.1	21
2.50	13.9	19
3.00	16.9	16
3.50	19.9	13
4.00	23.0	12
4.50	26.1	10

GENFLEX NAILBASE ISO

THICKNESS [INCHES]	LTTR	SHEETS PER BUNDLE
1.50	6.6	32
2.00	9.5	24
2.50	12.3	19
3.00	15.3	16
3.50	18.3	14
4.00	21.4	12
4.50	24.5	11

***Long-Term Thermal Resistance (LTTR-value)** means a 15-year time weighted average thermal resistance as determined in accordance with the LTTR test method

NOTE: Product availability and quantity may vary based on manufacturing facility.

