

# Product Data Sheet

## GenFlex EZ Peel & Stick Flashing

Item Description	Item Number
5½" x 100' (139.7 mm x 30.5 m) White	W590030085
5½" x 100' (139.7 mm x 30.5 m) Grey	W590030086
5½" x 100' (139.7 mm x 30.5 m) Tan	W5900LT30087
*2-rolls cover tape; stand up scrub pads and handle	

### Description

GenFlex EZ Peel & Stick Flashing consist of a white cured tape adhesive that is laminated to a white, grey, or tan thermoplastic cover strip. GenFlex EZ Peel & Stick Flashing may be used to cover Bar Anchors or strip in metal flanges.

### Method of Application

GenFlex Clear Primer must be applied with a scrub pad and handle when installing GenFlex EX Peel & Stick Flashing to GenFlex TPO Membranes.

The application of the GenFlex EX Peel & Stick Flashing should be as follows:

1. All sources of ignition should be eliminated; adequate ventilation should exist.
2. Thoroughly mix GenFlex Clear Primer. DO NOT THIN! A minimum of 2 minutes of vigorous hand mixing with a wooden paint stirrer or its equivalent is required.
3. Clean all surfaces with a clean cotton rag removing excess contamination prior to application of the primer.
4. With a scrub pad and handle, apply GenFlex Clear Primer to the TPO membrane and metal flange using long and continuous back and forth strokes with heavy to moderate pressure along the bonding area until no streaks or puddling occurs.
5. Allow GenFlex Clear Primer to dry until slightly tacky to a dry finger touch.
6. Center the GenFlex EX Peel & Stick Flashing over the fasteners used to secure the metal edge. Remove the release paper from the tape and apply the tape to the primed metal and TPO surfaces.
7. Using a silicone coated rubber or steel hand roller, hand-roll the entire length of the tape into the primed surface assuring adhesion.
8. Apply a continuous “high profile” bead of TPO Edge Caulk at Field seam Intersections, Cover Tape end laps, and edge metal joints. All caulking details will be completed per standard specifications with GenFlex Edge Caulk.

## Storage

- Store in original unopened container indoors at temperatures between 60 °F (16 °C) and 80 °F (27 °C). Do not store on roof in direct sunlight or at temperatures above 100 °F (38 °C). When exposed to lower temperatures, restore to room temperature prior to use.
- Do not store in direct sunlight or at temperatures above 80 °F (27 °C).
- When exposed to lower temperatures, restore to room temperature prior to use.

## Shelf Life

18 months; shelf life will be shortened if exposed to elevated temperatures.

## Precautions

- Take care when moving, transporting, and handling, etc. to avoid sources of punctures and physical damage.
- Contact GenFlex Systems Technical Department for specific recommendations.
- Refer to appropriate Product Data Sheets for additional information on other components contained within this kit.

## LEED® Information

Post-Consumer Recycled Content: 0%

Post Industrial Recycled Content: 0%

NOTE: LEED® is a registered trademark of the U.S. Green Building Council

Typical Properties – Tape		Typical Properties – TPO	
Property	Typical Value	Property	Typical Value
Color	White	Color	White, Grey, Tan (LT)
Base	Rubber Polymers	Base	TPO
Solids	100%	Solids	100%
Specific Gravity	0.98 ±0.02 H <sub>2</sub> O=1)	Specific Gravity	1.15 ±0.05
Cure State	Cured	Cure State	Cured
Width	5¾" – 0, + 1/16" (146 mm – 0 mm, + 1.62 mm)	Width	5½" + 0, + ⅛" (140 mm + 0 mm, + 3.18 mm)
Thickness	0.035" + 0.002", -0.005" (0.889 mm + 0.051 mm, -0.127 mm)	Thickness	0.030" ± 10% (0.76 mm)
Length	100 Lineal Feet -0, + 2' (30.5 m -0, + 0.61 m)	Length	100 Lineal Feet -0, + 2' (30.5 m -0, + 0.61 m)

Please contact Amrize Technical Services at 800-428-4511 for further information.

This sheet is meant to highlight GenFlex products and specifications and is subject to change without notice. Amrize takes responsibility for furnishing quality materials that meet published GenFlex product specifications or other technical documents, subject to normal manufacturing tolerances. Neither Amrize nor its representatives practice architecture. Amrize offers no opinion on and expressly refuses any responsibility for the soundness of any structure. Amrize accepts no liability for structural failure or resultant damages. Consult a competent structural engineer prior to installation if the structural soundness or structural ability to properly support a planned installation is in question. No Amrize representative is authorized to vary this disclaimer.